AQUA MAX® WATER-RESISTANT SOLVENT-FREE ASSEMBLY ADHESIVE AND SEALANT.





PRODUCT DESCRIPTION

Water-resistant solvent-free assembly adhesive and sealant based on SMP Polymer.

FIELD OF APPLICATION

For the bonding, assembly and sealing of almost all materials on almost all surfaces. Extremely suitable for swimming pool construction, ponds and agriculture.

Suitable for all kinds of applications in and around the swimming pool such as for skimmers, edges, tiles, drains, roofing, outflow pipes and dilatation joints. Furthermore, suitable for applications around ponds such as drains, conduits and pond edges. Even suitable for underwater applications Not suitable for PE, PP, PTFE, pure plaster and bitumen. When gluing plastics always perform an adhesion test first. Adhesion to plastics can vary depending on the type of synthetic and the quality of the plastic.

PROPERTIES

- · (Chlorine/sea) water resistant
- · UV resistant
- $\cdot \, \text{Very high final bond strength} \\$
- · Very high, permanent elasticity
- · Very good filling capacity
- $\cdot \, Good \, standing \, power \,$
- · Non-shrinking; 100% adhesive
- · Solvent-free
- · No soiling of joint edges
- \cdot Resistant to temperatures between -40°C and +100°C
- $\cdot \, Paintable \,$

PREPARATION

Working conditions: The ambient temperature, the adhesive and the materials to be bonded should be no less than $+5^{\circ}$ C.

Preliminary surface treatment: Surfaces must be clean, dust- and grease-free. Surface must be solid. The surface can be moist. Use of primer not required. **Tools:** Cartridge gun and rubber hammer.

APPLICATION

Coverage: With spot bonding: 5-8 m²/kg. Stripes: one cartridge issues approx. 8-15 metres of adhesive (depending on the diameter of the cut nozzle).

Directions for use:

BONDING: Cut off screw thread, assemble nozzle and cut to a diameter of at least 0.5 cm. Depending on the weight of the material, apply the adhesive evenly in vertical strips or dots at intervals of between 10 and 40 cm. Always apply adhesive to the corners and along the edges. Assemble materials with a pushing movement and press or knock firmly together. Correction is still possible. For heavy materials, fastenings or supports may be required. Close the cartridge properly immediately after use.

SEALING: Cut off screw thread, assemble nozzle and cut at an angle to the desired joint width. Apply the sealant to the bottom of the joint and tool within 10 minutes using a wet finger (water with washing up liquid without lemon), putty knife or sealant smoother. Close the cartridge properly immediately after use.

Stains/residue: Remove adhesive residues immediately with white spirit. Dry adhesive residue can only be removed mechanically.

Points of attention: Because of the continually changing water quality in swimming pools, it is not possible to indicate life expectancy when the product is in protracted contact with swimming pool water.

CURE TIMES

Skin over time: approx. 10 minutes **Cure rate:** approx. 2 mm/24 hrs

Full bond strength: Full bond strength after approx. 48 hours

 * Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Water resistance: Very good

Temperature resistance: From -40° C to $+100^{\circ}$ C.

UV resistance: Good

Chemicals resistance: Good

Paintability: Paintable with both acrylic and alkyd paints. With alkyd paint,

the drying time may be longer. Always test in advance.

Elasticity: Very good **Filling capacity:** Very good

TECHNICAL SPECIFICATIONS

Chemical base: SMP-Polymer

Colour: White **Viscosity:** Pasty

Solid contents: approx. 100 % **Density:** approx. 1.5 g/cm³

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

AQUA MAX®



Tensile strength: approx. 250 N/cm² Shear strength: approx. 320 N/cm²

Flash point: K3 (>55°C)
Shrinkage: approx. 0 %
Hardness (Shore A): approx. 60
Elongation of rupture: approx. 240 %

STORAGE CONDITIONS

A minimum of 18 months. Best Before Date (MM/YY): see packaging. Limited shelf life after opening. Store dry in sealed packaging between $+5^{\circ}$ C and $+25^{\circ}$ C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.