## **SILICONE NEUTRO**

### BOSTIK

### **NEUTRAL SILICONE SEALANT FOR ALL CONSTRUCTION SEALS**



#### PRODUCT DESCRIPTION

High quality neutral, permanently elastic, water resistant silicone sealant for all construction sealings.

#### **FIELD OF APPLICATION**

Suitable for sealing moving joints, dilatation and connection joints, seams and cracks in construction, houses, cars, boats and caravans. Ideal for synthetics (PVC door and window frames, polycarbonate and plexiglas domes), stone and masonry and (sensitive) metal (copper, zinc, iron, aluminium, brass, stainless steel). Universal adhesion without primer on all common building materials, such as concrete, stone, (natural) stone, ceramics, enamel, glass, metal, rubber, wood and synthetics (acrylic, PVC, ABS, polystyrene, polyester). Does not bond to bitumen, polyethylene, polypropylene and PTFE. Not suitable for aquariums, polyethylene (PE), polypropylene (PP), PTFE and bitumen.

#### **PROPERTIES**

- · Neutral, acid-free
- · (Sea)water resistant
- · 100% silicone
- $\cdot \, \text{Permanently elastic} \,$
- · Excellent bonding on all materials
- · Chemical resistant
- · Colourfast
- · UV and all-weather resistant
- · Resistant to temperatures between -50°C and +120°C
- · Easy to apply

#### **PREPARATION**

**Working conditions:** Only apply at temperatures between  $+5^{\circ}$ C and  $+40^{\circ}$ C. **Surface requirements:** The surface must be dry, clean and free of dust, rust

and grease.

**Preliminary surface treatment:** For a good result, cover the joint's edges with masking tape. If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

**Tools:** Apply cartridge contents with Bostik Click Gun. Multi Tool to open the cartridge and tooling the sealant.

#### **APPLICATION**

**Coverage:** Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

#### **Directions for use:**

Use sealant gun to handle cartridge. Open the cartridge by cutting off the plastic nipple on the top side at the screw thread with a sharp knife. Screw on the nozzle and chamfer at the desired width. Ensure a minimum joint width of 6 mm and a maximum of 20 mm. The joint depth depends on the joint width. Keep a joint depth of 6 mm up to a joint width of 12 mm. Beyond that, the joint depth should be half the joint width. Apply the sealant evenly into the joint, then within 10 minutes tool with a sealant smoother or Bostik Multi Tool moistened with a non-aggressive or mild soap solution. Remove the applied masking tape immediately after tooling. After approx. 15 minutes, a surface skin will form. Cured silicone sealant can only be removed mechanically. For aquariums use only Bison Silicone Sealant Glass.

**Stains/residue:** Immediately remove stains with white spirit. The cured sealant can be removed either mechanically or with Bostik silicone sealant residue remover.

**Advice:** Use Bostik Silicone Vetro Metallo for sealing aquariums.

Use Bostik Poly Max® for a paintable, water resistant and permanently elastic

**Points of attention:** Silicone hardens under the influence of humidity. Contact with humidity is therefore absolutely necessary during curing. Alijd consider a joint of at least 6 mm wide.

#### **CURE TIMES**

Cure rate: approx. 2 mm/24 hrs

\* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient

#### **TECHNICAL PROPERTIES**

Water resistance: Very good

**Temperature resistance:** From  $-50^{\circ}$ C to  $+120^{\circ}$ C.

UV resistance: Very good Mildew resistance: Very good Chemicals resistance: Very good

**Elasticity:** Very good **Filling capacity:** Good

#### **TECHNICAL SPECIFICATIONS**

Chemical base: Silicone elastomer

Colour: Brown

**Viscosity:** approx. 0 mPa.s., Pasty **Density:** approx. 1.01 g/cm<sup>3</sup>

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

# **SILICONE NEUTRO**



Hardness (Shore A): approx. 10 Elasticity E-modulus: approx. 0,26 MPa Elongation of rupture: approx. 250 %

#### **STORAGE CONDITIONS**

At least 15 months after production. Limited shelf life after opening. Store in properly sealed packaging in a dry place at between  $+5^{\circ}$ C and  $+25^{\circ}$ C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.