6150322 - GRIFFON KOLMAT® EASYFIT BOTTLE 50 ML ES/EN



KOLMAT® EASYFIT ES/EN SEALING AND SECURING AGENT FOR METAL THREADED CONNECTIONS



APPLICATION

Directions for use:

1) Apply evenly to the screw thread. 2) Assemble the connection and tighten securely. Joint is adjustable for about 1 minute. At low pressure, compound taxed directly. After curing heavy demountable.

Stains/residue: Remove any residue with a moist cloth or degreaser.

TECHNICAL PROPERTIES

Water resistance: Very good Temperature resistance: -50°C to +150°C. Chemicals resistance: Very good.

TECHNICAL SPECIFICATIONS

Chemical base: Methacrylate ester Colour: White Viscosity: approx. 2500 mPa.s. Density: approx. 1.08 g/cm³

STORAGE CONDITIONS

A minimum of 24 months. Limited shelf life after opening. Store in properly sealed packaging in a dry place at between $+5^{\circ}$ C and $+25^{\circ}$ C.

PRODUCT DESCRIPTION

Sealing and securing agent for metal threaded connections.

FIELD OF APPLICATION

For sealing and securing metal threaded connections in, e.g., gas, water, central heating and insutrial conduit systems. Suitable for, e.g., steel, brass and stainless steel.

PROPERTIES

· Immediately loadable at low pressure

- · Resistant to thermal shock and vibration
- · Chemical resistant

QUALITY LABELS/STANDARDS

Certificates: ACS: In accordance with the positive lists of ACS (Attestation de Conformité Sanitaire). Certificate IPL 14 CLP NY 010. Gastec QA: Screw thread sealant for gas-tight sealing of metal threaded pipe

joints, class 8 bar. Certificate Q 014/006 based on GASTEC QA demands 31-2. **Standards:** EN 751-1: Sealing materials for metallic threaded joints in contact with 1st, 2nd and 3rd family gasses and hot water. Part 1 Anaerobic compounds.

PREPARATION

Working conditions: Do not use in temperatures $\leq +5^{\circ}$ C. **Preliminary surface treatment:** Clean and degrease surfaces.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

150322 20