





**UV resistance:** Very good

**Chemicals resistance:** Very good

**Paintability:** Paintable with both acrylic and alkyd paints. The drying time may be longer with alkyd paints. Always test in advance.

**Elasticity:** Very good

## TECHNICAL SPECIFICATIONS

**Chemical base:** Polymer-modified, emulsified bitumen

**Colour:** Black

**Viscosity:** Liquid

**Solid contents:** approx. 60 %

**Density:** approx. 1.02 g/cm<sup>3</sup>

**Hardness (Shore A):** approx. 20

**Elongation of rupture:** approx. 900 %

## STORAGE CONDITIONS

A minimum of 24 months. Limited shelf life after opening. Properly sealed packages should be stored in a dry, cool, frost-proof location at temperatures between +5°C and +25°C.