

SUPERHIARO SPRAY

CONTACT SPRAY ADHESIVE



PRODUCT DESCRIPTION

Bostik Superhiaro Sprays a contact adhesive for large surface bonding. Bonds alternatively permanent or removable. Suitable for bonding various materials, also suitable for Styrofoam®. Even spray pattern – powerful glue application. Non-clog spray valve.

FIELD OF APPLICATION

For bonding paper, cardboard, collages, metal foils, leather, felt, many plastics, textiles, Styrofoam® etc. with themselves and many other materials such as wood, ceramics, glass etc. Not suitable for PE, PP.

PROPERTIES

- Universal
- Strong
- Fast
- Bonds alternatively:
 1. permanent
 2. removable

PREPARATION

Working conditions: Not to be applied at temperatures below +10°C.

Personal safety: Spray adhesive contains volatile, highly flammable solvents. Appropriate precautions should be taken when using and storing this product. When applying product to larger surfaces, ensure good ventilation in the working area.

Surface requirements: The areas to be glued must be dry and free of any dust or grease.

APPLICATION

Coverage: 5 m²/l, applied double sided

Directions for use:

Shake aerosol spray can well prior to use.

Rock solid bond: Immediate fixation: Apply adhesive to both sides. Allow to dry for at least 10 minutes, join parts and press or tap. No adjustments possible. **Adjustable fixation:** It is also possible to apply adhesive to one side and join the parts immediately. Adjustments are possible within 5 minutes, approx. drying time 24 hours.

Reusable bond: Apply adhesive to one side (not the substrate). Allow to dry for at least 20 minutes, join parts and press well. The bonded object is now self-adhesive and can be removed and fixed again.

After spraying, hold can upside down and press spray head until only propellant and no more adhesive comes out. This prevents clogging up of spray can.

Stains/residue: Remove fresh stains immediately with benzene. Let dried stains soak in benzene.

Points of attention: The technical data provided apply to the base adhesive without propellant.

TECHNICAL PROPERTIES

Moisture resistance: Good

TECHNICAL SPECIFICATIONS

Colour: Transparent

Viscosity: Runny

Solid contents: approx. 22 %

Density: approx. 0.72 g/cm³

STORAGE CONDITIONS

At least 24 months after date of manufacture. Limited shelf life after opening. Store in a dry, cool and frost free place.