SILICONE VETRO METALLO

BOSTIK

WATER-RESISTANT AND PERMANENTLY ELASTIC SILICONE SEALANT



PRODUCT DESCRIPTION

High quality and permanently elastic silicone sealant on acetic acid basis. Especially for the water resistant sealing of joints, seams and cracks in glass and metal, in combination with another material. UV and all-weather resistant. Can be used internally and externally.

FIELD OF APPLICATION

Suitable for the sealing of joints, seams and cracks in glass and metal, in combination with another material. For sealing joints, seams and cracks in the house, glass construction, display case construction, car, boat and caravan. Especially suitable for bonding and sealing clear glass, frameless aquariums, display cases, display windows, glass terrariums, water basins and (double) glass constructions. Adheres to clear glass (non-coated, single-layered), ceramics, glazed tiles, enamel, metal (including aluminium) and various synthetics. Not suitable for polyethylene (PE), polypropylene (PP), PTFE and bitumen.

PROPERTIES

- · Water resistant
- $\cdot \, \text{Permanently elastic} \,$
- \cdot UV and all-weather resistant
- · Excellent bonding without primer
- $\cdot \, \text{Chemical resistant} \\$
- · Easy to apply
- · Colourfast

PREPARATION

Working conditions: Only apply at temperatures between $+5^{\circ}$ C and $+40^{\circ}$ C. **Surface requirements:** The surface must be dry, clean and free of dust, rust and grease.

Preliminary surface treatment: Sand synthetics lightly with sandpaper. For a good result, cover the joint's edges with masking tape. In order to prevent three-sided bonding and to ensure the right joint depth, fill joints with a foam backer rod or PE film.

Tools: Apply cartridge contents with Bostik Click Gun. Multi Tool to open the cartridge and tooling the sealant.

APPLICATION

Coverage: Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

Directions for use:

Use sealant gun to handle cartridge. Open the cartridge by cutting off the plastic nipple on the top side at the screw thread with a sharp knife. Screw on the nozzle and chamfer at the desired width. Ensure a minimum joint width of 4 mm and a maximum of 25 mm. The joint depth depends on the joint width. Keep a joint depth of 6 mm up to a joint width of 12 mm. Beyond that, the joint depth should be half the joint width. Inject the sealant evenly into the joint and tool within 10 minutes with a putty knife or finger, moistened with a soap solution.

Stains/residue: Remove wet stains immediately with white spirit. Cured sealant can only be removed mechanically.

Advice: Use Bostik Silicone Sanitari for sanitary sealings.

Use Bostik Poly Max® for a paintable, water resistant and permanently elastic

Points of attention: Ensure the joint remains dry for at least the first 8 hours.

When used in aquariums or terrariums, ventilate well for 4-8 days and then completely fill with water 3 to 4 times (each time for 24 hours) before planting or populating with fish.

CURE TIMES

Skin over time: approx. 10-15 minutes **Cure rate:** approx. 3 mm/24 hrs

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Water resistance: Very good
UV resistance: Very good

Chemicals resistance: Very good

Elasticity: Very good **Filling capacity:** Very good

TECHNICAL SPECIFICATIONS

Colour: Transparent

Viscosity: approx. 0 mPa.s., Pasty Density: approx. 1.04 g/cm³ Hardness (Shore A): approx. 25

Elasticity E-modulus: approx. 0,45 MPa **Elongation of rupture:** approx. 480 %

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

SILICONE VETRO METALLO



STORAGE CONDITIONS

At least 24 months after date of manufacture. Limited shelf life after opening. Store in properly sealed packaging in a dry place at between $+5^{\circ}$ C and $+25^{\circ}$ C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.