



# AC EDILIZIA

## PAINTABLE SEALANT



**Surface requirements:** The surface must be dry, clean and free of dust, rust and grease.

**Preliminary surface treatment:** For a better adhesion on porous (highly porous) substrates, they should be first covered with a diluted acrylic solution (1 part sealant to 2 parts water). For a good result, cover the joint's edges with masking tape. Ensure a minimum joint width of 6 mm. Up to a joint width of 12 mm, ensure a joint depth of 6 mm. In case of wider joint widths, the joint depth should be half the joint width. Remove masking tape immediately after tooling.

### APPLICATION

**Points of attention:** The sealant dries transparent. The sealant is paintable upon complete curing

### STORAGE CONDITIONS

Store in well-sealed packaging in a cool, dry and frost free place.

### PRODUCT DESCRIPTION

Professional, paintable and elasto-plastic sealant based on acrylic dispersion. For sealing (lightly moving) joints, seams, cracks and tears. UV resistant, very easy to apply and easy to tool.

### FIELD OF APPLICATION

Suitable for sealing of slightly working joints, seams and cracks For internal use. Very suitable for seals around door and window frames, window sills, prefabricated elements, stairs, baseboards, walls, drywalls, ceilings, corrugated iron and conduits. Bonds to brick, (cellular) concrete, masonry, plasterwork, wood, ceramic tiles, metal and rigid PVC. Also suitable for sealing small cracks and cracks in walls. Not suitable for bitumen, polyethylene (PE), polypropylene (PP), PTFE and silicone.

### PROPERTIES

- Paintable
- Easy to tool
- Easy to apply
- Moisture resistant
- Excellent bonding without primer
- Very good sprayability
- Waterproof once fully cured
- UV and all-weather resistant
- Can be used internally and externally
- Permanently elasto-plastic (max. 12.5% stretch)
- Resistant to temperatures between -20°C and +75°C

### PREPARATION

**Working conditions:** Only apply at temperatures between +5°C and +40°C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.