GRIZZLY MONTAGE POWER SUPER STRONG AND FAST CONSTRUCTION ADHESIVE WITH HIGH INITIAL TACK AND HIGH FINAL STRENGTH FOR INTERIOR USE.



PRODUCT DESCRIPTION

Universal, super strong and fast construction adhesive for interior use, with high initial tack (500KG/M² in 10 seconds) and high final strength (60KG/CM² in 24 hours). For bonding all kinds of objects onto porous surfaces.

FIELD OF APPLICATION

Suitable for all kinds of materials: e.g. wood, Trespa[®], iron, aluminum, zinc, (stainless) steel, and other metals, stone, ceramic, concrete, brick, plaster, glass, PVC, ABS, PC, PMMA and other synthetic materials (test in advance), cork and polystyrene foam on porous surfaces like wood, stone, concrete, plaster and chipboard.

To all kinds of objects: e.g. skirting boards, laths, window sills, tear plates, thresholds, fascia boards, plate material, insulation material, stair steps, sheeting material, floorboards, plasterboard, ceramic tiles and polystyrene ornaments and borders. Not suitable for PE, PP, PTFE, bitumen, permanently moist places and for attaching a non-porous material on a non-porous substrate. When gluing plastics always perform an adhesion test first. Adhesion to plastics can vary depending on the type of synthetic and the quality of the plastic.

PROPERTIES

- \cdot High initial tack (500KG/M² in 10 seconds)
- High final strength (60KG/CM² in 24 hours)
- \cdot For all materials
- \cdot Suitable for porous and uneven surfaces
- \cdot For interior use
- · Easy to apply
- Filling
- $\cdot \, \text{Solvent-free}$
- · Permanently elastic
- · Correctable
- · Moisture resistant
- · Temperature resistant

PREPARATION

Working conditions: Only apply at temperatures between $+5^{\circ}$ C and $+40^{\circ}$ C. **Surface requirements:** Both parts must be dry, clean and free of dust and grease. One of the two parts must be porous (absorbent).

Tools: Apply cartridge contents using a sealant gun (a Bostik Power Pistol, for example). If necessary, use a rubber mallet to tap lightly. For surface bonding use a glue spreader (2 mm).

APPLICATION

Directions for use:

Before using open cartridge at the top by cutting off the plastic nipple above the thread with a Bostik multitool. Fix the nozzle onto the cartridge and cut at an angle to the desired diameter. Apply one sided on a sturdy, clean and dustand grease free surface. Apply in dots or stripes (10-40 cm). Firmly press or tap and leave to harden. Support heavy materials for 10 seconds. Remove excess adhesive immediately with ammonia. Final strength after 24 hours depending on surface and conditions.

Stains/residue: Use water for cleaning tools and removing wet adhesive residue. Dry adhesive residue can only be removed mechanically. **Advice:** We recommend Bostik Grizzly Montage Power for interior use.

CURE TIMES*

Drying/Curing time: approx. 10 sec for initial tack **Final bonding strength after:** approx. 24 hours

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Moisture resistance: Good Water resistance: Limited Temperature resistance: -20°C - +80°C UV resistance: Very good Chemicals resistance: Good Paintability: Very good Elasticity: Good Filling capacity: Good

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

5314009 202010

GRIZZLY MONTAGE POWER SUPER STRONG AND FAST CONSTRUCTION ADHESIVE WITH HIGH INITIAL TACK AND HIGH FINAL STRENGTH FOR INTERIOR USE.

TECHNICAL SPECIFICATIONS

BO

Chemical base: Acrylic dispersion Colour: White Viscosity: approx. Pasty Solid matter: approx. 65 % Density: approx. 1.28 g/cm³ Initial bond strength: approx. 0.5 N/cm² Shear strength: approx. 600 N/cm² Shrinkage: approx. 35 %

STORAGE CONDITIONS

Close container properly and store in a dry, cool and frost-freeplace.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.

6314009 20201030